



Formosa Plastics®

Formolene® HDPE

Technical Data Sheet

Formolene HP4401

Melt Index – 0.11

Density – 0.944

High Density Hexene Copolymer

Formolene HP4401 is a high performance copolymer that is designed for the most demanding requirements of pressure pipe applications. It has good long-term hoop strength performance, very high melt strength, outstanding toughness even at low temperatures.

Formolene HP4401 meets all requirements of ASTM D4976 – PE 235.

When blended with the approved color concentrates, Formolene HP4401 has a cell class of 345464C per ASTM D3350-05, is listed by PPI as a PE3608 material with HDB's of 1,600 psi @ 73°F and 800 psi @ 140°F and meets the requirements of NSF Standard 14/61 for use with potable water. HP4401 also qualifies as a PE3408 material under the old ASTM D3350-02a and PPI standards. HP4401 also qualifies as a PE80 material per ISO 9080.

Suggested Applications

Potable water, Oil and gas gathering and distribution, Chemical, Industrial and mining, Sewer

Nominal Physical Properties

PROPERTY** (Natural Resin)	TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density (Natural)	D1505	g/cc	0.944	g/cc	0.944
(Black)			0.955		0.955
Melt Index,	D1238	g/10 min.	0.11	g/10 min.	0.11
Condition E, 190°C/2.16 kg (MI)			12.0		12.0
Condition F, 190°C/21.6 kg (HLMI)					
Environmental Stress Crack Resistance (ESCR)	D1693	h	>1000	h	>1000
Condition A, B, C (100% Igepal), F ₅₀					
Tensile Yield Strength,	D638	psi	3200	MPa	22
@ Yield			Type IV		5000
@ Break	D638	%	>500	%	>500
2" (50 mm) per min.			Type IV		
Ultimate Elongation,	D3350	psi	110,000	MPa	760
2" (50 mm) per min.			D790		140,000
Flexural Modulus	D746	°F	<-130	°C	<-90
Brittleness Temperature	F1473	h	150	h	150
Pent Slow Crack Growth					

* Our licensor does not warrant or imply that this product meets their specifications for HHM TR 480Z.

** Physical properties reported herein were determined on compression molded specimens prepared in accordance with Procedure C of ASTM D1928 THE NOMINAL PROPERTIES REPORTED HEREIN ARE TYPICAL OF THE PRODUCT BUT DO NOT REFLECT NORMAL TESTING VARIANCE AND THEREFORE SHOULD NOT BE USED FOR SPECIFICATION PURPOSES.

Published 02/05 Rev. 03/07

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 716-7230

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

Printed in the the USA on recycled paper

Formolene® is a registered trademark of FPC USA

©Formosa Plastics Corporation, U.S.A.



ISO 9001:2000
FS 70459
FM 31429
FM 68976



ISO 14001
EMS 35710

