

RELENE B 56003

BLOW MOULDING GRADE

Relene B 56003 is a High Density Polyethylene grade suitable for general purpose extrusion blow moulding applications. Articles blown from this grade exhibit good stiffness. The resin offers good melt strength, ESCR and impact resistance & typically used for packaging of oil, vanaspati, general purpose containers, jerry can etc.

Physical Characteristics :

<u>Property</u>	<u>Unit</u>	<u>Test Method</u>	<u>Value</u>
Density	g/cc	ASTM D 1505	0.956
MFI (2.16 kg)	g/10 min	ASTM D 1238	0.30

Typical Properties :

<u>Property</u>	<u>Unit</u>	<u>Test Method</u>	<u>Value</u>
Tensile Strength at Yield	MPa	ASTM D 638	26
Elongation at break	%	ASTM D 638	550
Flexural Yield Strength	MPa	ASTM D 790	28.5
Flexural Modulus	MPa	ASTM D 790	900
Hardness	Shore D	ASTM D 2240	69
Vicat Softening Point	°C	ASTM D 1525	128

Processing with Relene B 56003 :

- Melt temperature in range of 175 - 205°C are recommended.
- Normally, temperature of 190 - 205°C will result in optimum ESCR properties

PE 0901

** Typical values with injection moulded specimens, not to be taken as specification*

HDPE grade Relene B 56003 meets the requirements stipulated in standard IS:10146-1982 on “Specifications for Polyethylene for its safe use in contact with foodstuffs, pharmaceuticals and drinking water”. It also conforms to the positive list of constituents as prescribed in IS:10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, olefin Polymer.

The information and data presented herein is true and accurate to the best of our knowledge. Now warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or local.

The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorized agent, as the information and/or data is subject to change based on the research and development work undertaken by the company.

RELENE/RELCAIR™ is the trade name of Polyethylene from Reliance Industries Limited.