



SABIC® PP 525P

PP homopolymer for Bi-axially oriented film

Description:

SABIC® PP 525P is a non formulated grade, specially developed for biaxially oriented PP (BOPP) film extrusion with a very specific molecular structure providing the ultimate properties required for the stenter film process.

Application:

SABIC® PP 525P is applied as core layer in coextruded film and/or as base material in plain film.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

Typical values

Revision 20060221

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	3.0	ISO 1133
Density	kg/m ³	905	ISO 1183
Molecular Weight Distribution	-	Broad	SABIC method
Isotacticity	-	Medium	SABIC method
Formulation			
Anti block agent	-	No	SABIC method
Slip agent	-	No	SABIC method
Anti static agent	-	No	SABIC method
Nucleating agent	-	No	SABIC method
Gas fading stabilized	-	No	SABIC method
Mechanical properties			
Tensile test			ISO 527
stress at yield	MPa	41	
stress at break	MPa	36	
strain at break	%	600	
Flexural test			ASTM D 790
Flexural modulus	MPa	1500	
Thermal properties			
Vicat softening temperature			
at 10 N (VST/A)	°C	153	ISO 306/A
at 50 N (VST/B)	°C	79	ISO 306/B

All information supplied by or on behalf of any of the SABIC Europe companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC Europe company assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to any of the SABIC Europe companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.